

DuPont™ Neoprene Fluid Resistance at Room Temperature

Technical Information — Rev. 1, July 2010

Chemical	Rating
Acetic acid, 30%	A
Acetic acid, glacial	B
Acetic anhydride	A
Acetone	B
Acetylene	B
Aluminum chloride solutions	A
Aluminum sulfate solutions, 70 °C [158 °F]	A
Ammonia, anhydrous	A
Ammonium chloride solutions	A
Ammonium hydroxide solutions, 70 °C [158 °F]	A
Ammonium sulfate solutions, 70 °C [158 °F]	A
Amyl acetate	C
Amyl alcohol, 70 °C [158 °F]	A
Aniline	C
ASTM hydrocarbon test fluid	X
ASTM oil #1	A
ASTM oil #3, 70 °C [158 °F]	B
ASTM reference fuel A	A
ASTM reference fuel B	C
ASTM reference fuel C	C
Asphalt	B
Barium hydroxide solutions, 70 °C [158 °F]	A
Benzaldehyde	C
Benzene	C
Benzoyl chloride	C

Chemical	Rating
Borax solutions, 70 °C [158 °F]	A
Borax acid solutions 70 °C [158 °F]	A
Bromine, anhydrous liquid	C
Butane	A
Butyl acetate	C
Butyraldehyde	B
Butyric acid	C
Calcium bisulfite solutions, 93 °C [200 °F]	A
Calcium chloride solutions	A
Calcium hydroxide solutions, 70 °C [158 °F]	A
Calcium hypochlorite, 5%	B
Calcium hypochlorite	X
Carbon bisulfide	C
Carbon dioxide	A
Carbon monoxide	A
Carbon tetrachloride	C
Castor oil, 70 °C [158 °F]	A
Chlorine gas, dry	B
Chlorine gas, wet	C
Chloroacetic acid	A
Chlorobenzene	X
Chloroform	C
Cholorsulfonic acid	C
Chromic acid, 10-50%	C
Citric acid solutions	A
Copper chloride solutions	A
Copper sulfate solutions	A



The miracles of science™

Chemical	Rating
Cottonseed oil	A
Creosote oil	C
Cyclohexane	C
Dibutyl phthalate	C
Diethyl sebacate	C
Diethyl phthalate	C
Dowtherm A	B
Ethyl acetate	C
Ethyl alcohol, 70 °C [158 °F]	A
Ethyl chloride	B
Ethyl ether	C
Ethylene dichloride 49 °C [120 °F]	C
Ethylene glycol, 70 °C [158 °F]	A
Ethylene oxide	X
Ferric chloride solutions	A
Fluosilici acid, 70 °C [158 °F]	A
Formaldehyde, 40%	A
Formaldehyde, 40%, 70 °C [158 °F]	C
Formic acid	A
Freon® 11	A-B
Freon® 11, 54 °C [130 °F]	B
Freon® 12	A
Freon® 12, 54 °C [130 °F]	A
Freon® 22	A
Freon® 22, 54 °C [130 °F]	A
Freon® 113	A
Freon® 113, 54 °C [130 °F]	A
Freon® 114	A
Freon® 114, 54 °C [130 °F]	T
Fuel oil	A
Furfural	B
Gasoline	B
Glue, 70 °C [158 °F]	A
Glycerin, 70 °C [158 °F]	A
n-Hexane	A
Hydraulic oils	A
Hydrochloric acid, 20%	A
Hydrochloric acid, 37%	A
Hydrochloric acid, 37%, 70 °C [158 °F]	B

Chemical	Rating
Hydrocyanic acid	A
Hydrofluoric acid, 48%	A
Hydrofluoric acid, 75%	T
Hydrogen	A
Hydrogen peroxide, 88-1/2%	B
Hydrogen sulfide	A
Isooctane	A
Isopropyl alcohol	A
Isopropyl ether	C
JP-4	C
JP-5	X
JP-6	X
Kerosene	B
Lacquer solvents	C
Lactic acid	A
Linseed oil	A
Lubricating oils, 70 °C [158 °F]	B
Magnesium chloride solutions, 70 °C [158 °F]	A
Magnesium chloride solutions, 70 °C [158 °F]	A
Mercuric chloride solutions	A
Mercury	A
Methyl alcohol, 70 °C [158 °F]	A
Methyl ethyl ketone	X
Methylene chloride, 212 °C [100 °F]	C
Mineral oil	A
Mixed acids	X
Naphtha	C
Naphthalene, 80 °C [176 °F]	C
Nitric acid, 10%	B
Nitric acid, 30%	C
Nitric acid, 60%	X
Nitric acid, 70%	C
Nitric acid, red fuming	C
Nitrobenzene	C
Oleic acid	B
Oleum, 20%	C
Palmitic acid, 70 °C [158 °F]	B
Perchloroethylene	X

Chemical	Rating	Chemical	Rating
Phenol	B	Sulfur dioxide, gas	A
Phosphoric acid, 20%	T	Sulfur trioxide	C
Phosphoric acid, 60%	A	Sulfuric acid, up to 50%, 70 °C [158 °F]	A
Phosphoric acid, 70%	T	Sulfuric acid, 60%	A
Phosphoric acid, 85%	A	Sulfuric acid, 90%	X
Pickling solution, 20% nitric acid, 4% HF	B-C	Sulfuric acid, 95%	C
Pickling solution, 17% nitric acid, 4% HF	X	Sulfuric acid, fuming, 20% oleum	C
Picric acid	A	Sulfurous acid	X
Potassium dichromate solutions	A	Tannic acid, 10%	A
Potassium hydroxide solutions, 70 °C [158 °F]	A	Tartaric acid	A
Pydraul, 312 °C [154 °F]	C	Toluene	C
Pyridine	X	Tributyl phosphate	C
SAE #10 oil	C	Trichloroethylene	C
Skydrol 500	C	Tricresyl phosphate solutions	T
Shell turbine oil 307	T	Triethanolamine, 70 °C [158 °F]	A
Silicone grease	A	Trisodium phosphate solutions	T
Skydrol 500	C	Tung Oil	A
Soap Solutions, 70 °C [158 °F]	A	Turpentine	C
Sodium chloride solutions	A	Water, 100 °C [212 °F]	A
Sodium dichromate, 20%	B	Xylene	X
Sodium hydroxide, 46%, 70 °C [158 °F]	A	Zinc chloride solutions	A
Sodium hydroxide, 50%	A		
Sodium hydroxide, 73%	T		
Sodium hypochlorite, 20%	B		
Sodium peroxide solutions	A		
Soybean oil	A		
Stannic chloride	B		
Stannous chloride, 15%, 70 °C [158 °F]	A		
Steric acid, 70 °C [158 °F]	B		
Sulfur, molten	A		
Sulfur dioxide, liquid	A		

Key:

A Fluid has little or no effect

B Fluid has minor to moderate effect

C Fluid has severe effect

T No data: likely to be compatible

X No data: not likely to be compatible

Unless otherwise noted, concentrations of aqueous solutions are saturated. All ratings are at room temperature unless specified.

This tabulation is based on laboratory tests and records of actual service performance. It should be used as a guide only. Neoprene's degree of compatibility with a particular fluid in a given application will depend on variables such as temperature, aeration, velocity of flow, duration of exposure, stability of the fluid, degree of contact, etc. For this reason, it is always advisable to test the material under actual service conditions before specification. If this is not practical test should be devised which simulate service conditions as closely as possible.

Visit us at neoprene.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2010 DuPont. The DuPont Oval Logo, DuPont™, and The miracles of science™ are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(08/03) Reference No. NPE-A10435-00-B0710



The miracles of science™